



PRODUCT DATA SHEET

NORGLASS LABORATORIES PTY.LTD.
A.B.N. 92 001 807 245
P.O. Box 312, Neutral Bay. NSW 2089 Australia
59 Moxon Road, Punchbowl NSW
Ph: 61 2 9708 2200 Fax: 61 2 9796 3069
Email: norglass@bigpond.net.au
www.norglass.com.au



STAYBOND EPOXY GLUE

DESCRIPTION: A non staining gap filling, 2 pack epoxy adhesive of exceptionally high strength and cohesive value.

USES: As a waterproof, structural glue for boatbuilding and laminating work. Also used for bonding fibreglass, metals, concrete, ceramics and glass to themselves or to dissimilar materials.

PROPERTIES (At 20°C)

COLOUR: Translucent cream

TOXICITY: See Precautions

FINISH: Non staining, light amber

COVERAGE: 1 mixed litre = 1000cu.cm. (1 mixed litre will cover 1m² at 1mm thick)

DRYING TIME: Workable after 24 hours. Full cure 7 days

RECOATING: N/A

POT LIFE: 30 minutes at 50% relative humidity (subject to mass). Storage life minimum of 5 years if correctly sealed. NOTE: The hardener deteriorates quickly if not sealed properly.

MIXING RATIO: 1:1 by volume.

THINNING: NOT BE THINNED UNDER ANY CIRCUMSTANCES.

WEIGHT/LITRE: 0.95kg when mixed

VOLUME SOLIDS: Exceeds 99%

FLASH POINT: Non volatile

CLEAN UP: NORGLASS EPOXY THINNER

U.N. NUMBER: FREE

PREPARATION**TIMBER:**

Remove all forms of grease, oil, water or other contaminants.

Sand timber at 45degrees to the grain. Vacuum off all sanding dust from the grain.

This is essential for adhesion.

Wipe over the surface to be glued with Acetone or Methylated spirits on a clean cloth and allow to dry.

Oily timbers such as teak should be wiped down with NORGLASS ACETONE to remove surface oils, and be coated with STAYBOND EPOXY GLUE within 20 minutes.

If left too long, more oil will rise to the surface of the timber reducing the overall adhesion.

OTHER SURFACES:

All other substrates should be sandblasted or thoroughly solvent cleaned to ensure positive bonding.

APPLICATION:

Scoop out an equal volume of STAYBOND Base and Hardener (using separate spatulas) onto a mixing board and blend together thoroughly.

Blending or mixing should be done with a stick or spatula **not contaminated with either base or hardener. Mark each appropriately.**

Mix together until a creamy paste is achieved and no sign of unblended material remains. (streakiness)

Note: Under **no** circumstances can the mixing ratio of 1:1 by volume be altered or other extenders be added to the mix. Adding **excess Hardener** will make the mix rubbery not set it off quicker.

In cold weather prewarm both components by standing the cans in hot water for 15 minutes before mixing.

TRANSPORTATION:

Non Dangerous Goods.

36Kg	7.6Kg	3.8Kg	1.9Kg	950g	470g	200g
(40L)	(8L)	(4L)	(2L)	(1L)	(500ml)	(250ml)

PRECAUTIONS:

Do not attempt to glue when the **surface temperature** is below 10degreesC or when the temperature is likely to fall to that point during the first 12 hours of glueing.

Replace lids to both cans tightly when not in use.

Do not glue to charred or blackened timbers caused by burning off or high speed sanding. These areas must be planed or re-dressed before glueing.

Provide adequate ventilation during use. Avoid contact with skin and eyes and do not smoke or eat without thorough washing.

If a rash or swelling occurs, cease using the product immediately, Leave the area and consult a doctor.

Do not leave the lid off the hardener as this product deteriorates rapidly when left exposed to air and/or humid conditions, rendering the product ineffective.

FIRST AID:

If poisoning occurs contact a doctor or Poisons Information Centre on 131 126

DO NOT induce vomiting.

Give plenty of milk or water.

SPECIAL INSTRUCTIONS:

Cramping times should be at least 48 hours at 20degreesC.

Note: Do not starve joints of glue by over cramping (especially on open grained timbers). Remove all exuded glue before setting begins.

Complies with British Standards 1204 parts 1 & 2 for water and boil proof criteria.