

PRODUCT DATA SHEET

NORGLASS LABORATORIES PTY.LTD.
A.B.N. 92 001 807 245
P.O. Box 312, Neutral Bay. NSW 2089 Australia
59 Moxon Road, Punchbowl NSW
Ph: 61 2 9708 2200 Fax: 61 2 9796 3069
Email: norglass@bigpond.net.au
www.norglass.com.au



WEATHERFAST PREMIUM ENAMEL

DESCRIPTION: A single pack, low odour, high gloss enamel with excellent weathering characteristics and gloss retention in salt laden environments.

USES: Can be used on most surfaces including timber, steel, aluminium, concrete. For all areas of severe exposure, and interior applications.
Not recommended for areas of continuous immersion. Note: Area should be primed first with the appropriate primer.

PROPERTIES (at 20°C)

COLOUR:	16 standard colours, plus White & Black.
TOXICITY:	See "Precautions".
FINISH:	High gloss.
COVERAGE:	10 - 12 square meters per litre.
DRYING TIME:	Touch dry - 2 hours at 50% relative humidity.
RECOATING:	After 16 hours.
POT LIFE:	N/A
MIXING RATIO:	N/A
THINNING:	See "Application" section.
WEIGHT/LITRE:	1.19kg (White).
VOLUME SOLIDS:	51%(White), varies with colours
FLASH POINT:	32°C.
CLEAN UP:	Weatherfast Brushing or Spraying Thinners
U.N. NUMBER:	1263

- PREPARATION:** **New Timber** – Prime with NORGLASS PRi-COAT and follow with A further 1-2 coats, allowing 24 hours (minimum) drying between coats. Finish with 2 coats of Weatherfast Premium Enamel.
OTHER SUBSTRATES: Refer to appropriate NORGLASS product Information sheets.
Previously painted surfaces – require cleaning down with NORCLEAN-PLUS and removal of flaking or unsound paint. Sand with 280-360 grit sandpaper to remove any existing gloss.
- APPLICATION:** Stir contents before use.
Apply by brush, short nap roller or by spray.
In hot weather a maximum of 3% Weatherfast Brushing Thinners may be added to assist flow.
For conventional spray equipment, use 25-33½% of Weatherfast Spraying Thinners, or according to the spraying equipment used.
- TRANSPORTATION:** Dangerous Goods class 3.2
Flammable liquid.
Sizes available: 4 litre, 1 litre, 500ml, 250ml and 100ml. (White available in 10litre & 2litre.)
- PRECAUTIONS;** Provide adequate ventilation during use.
Flammable liquid – keep away from flames, excessive heat and sparks.
Wear correct apparatus when applying by spray.
Do not smoke.
Do not use on areas of constant immersion.
- The use of yellows and oranges are notoriously difficult to obtain coverage when applied over a less than uniform background. Any patchy areas will still show through after several coats of Northane or Weatherfast enamel. This is a problem with all yellow and orange lead free pigments regardless of manufacturer. The only solution is to make sure the background colour is completely uniform before painting i.e. uniformly white, grey, blue Etc.**
- FIRST AID:** If poisoning occurs call a doctor or Poisons Information Centre (Aust) on 13 11 26 or (NZ) 0800 764 766 and have label information ready.
If swallowed DO NOT induce vomiting. Give large quantities of water or milk. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and consult a doctor. Remove contact lenses if present and easy to do and continue rinsing. If skin contact causes irritation, remove contaminated clothing and wash skin thoroughly. If breathing difficulty arises remove to fresh air. Apply artificial respiration if not breathing.
- SPECIAL INSTRUCTIONS:** Do not use this product below 10degrees C as drying and gloss will be affected. Screen external surfaces away from dew for A minimum of 6 hours after painting.