

PRODUCT DATA SHEET

NORGLASS LABORATORIES PTY.LTD.
A.B.N. 92 001 807 245
P.O. Box 312, Neutral Bay. NSW 2089 Australia
59 Moxon Road, Punchbowl NSW
Ph: 61 2 9708 2200 Fax: 61 2 9796 3069
Email: norglass@bigpond.net.au
www.norglass.com.au



NORGLASS PAVING PAINT (SLIP RESISTANT & SMOOTH)

DESCRIPTION: A fast drying, low-odour, low-sheen finish with plastic granules incorporated into the coating for positive traction when wet. Can be applied to clean, dry, bare fibro, concrete, or timber without priming. Easily recoated.

PROPERTIES (at 20°C)

SLIP RESISTANCE: Slip Resistant paving paint conforms to a slip resistant rating of P5

COLOURS: Clay, Terracotta, Slate, Russet, Lincoln Green, Pewter, Sand, Ironbark, Safety Yellow and Ivory. Colours can also be intermixed with each other or Ivory to reduce intensity.

TOXICITY: N/A

FINISH: Low-sheen.

COVERAGE: 7-8 square metres/litre on untreated smooth surfaces; 8 - 9 square metres/litre on sealed smooth areas. On rough surfaces allow more paint.

DRYING TIME: Touch dry in 2 hours at 20°C

RECOATING: Re-coatable after 4 hours 25°C. Light traffic after 8 hours and 24 hours for normal use. For heavy commercial use allow 7 days.

POT LIFE: N/A

MIXING RATIO: N/A

THINNING: Not normally recommended, but up to 5% of Weatherfast Brushing Thinner can be added in hot weather. (i.e. 50mls per litre)

WEIGHT/LITRE: 1.22kg.

FLASH POINT: 32 °C.

CLEAN UP: Weatherfast Brushing Thinner or Weatherfast Spraying Thinners

UN NUMBER: 1263

PREPARATION: Prime bare timber with Norglass Pri-Coat and allow to dry, for other surfaces use Norglass Shipshape Primer Undercoat according to directions. Raw Steel or aluminium use Metal Etch prior to priming with Shipshape. Unpainted concrete must be washed with Norglass Concrete and Ceramic Cleaner, hosed off and allowed to dry thoroughly before painting. Fibreglass should be sanded, cleaned with Norclean-Plus and primed with Shipshape. Where a texture is to be painted, scrub down slip resistant surfaces with a domestic dishwashing liquid using warm water. Hose off thoroughly with fresh water and allow to dry, wipe over with Norclean-Plus. Prime with Shipshape. Sand previously painted slip resistant surfaces with a 240 grit sandpaper, remove the dust and clean with Norclean-Plus. Sand off any unsound, flaking or powdery paint, clean with Norclean-Plus before proceeding.

APPLICATION: Normally by brush and short nap Roller. However spraying can be done using HVLP spray equipment where conditions are suitable. Thin sparingly with Weatherfast Spraying Thinners. When rolling it is advisable to use the roller in one direction only to obtain a uniform deposition of granules. Work systematically to maintain a wet edge (where possible)

SPECIAL NOTE: **Where the gradient is steep, (greater than 1 in 12) you must contact NORGLASS TECHNICAL ADVISORY SERVICE before applying.**

TRANSPORTATION: Flammable liquid.
Dangerous Goods Class 3.2
Sizes available: 20litre, 10litre, 4litre, 1litre

PRECAUTIONS: Provide adequate ventilation during use.
Do not smoke and keep away from naked flames.
On very dry concrete surfaces a third coat may be required to produce an even result due to absorption.
Do not use on areas of constant immersion.

FIRST AID: If poisoning occurs call a doctor or Poisons Information Centre (Aust) on 13 11 26 or (NZ) 0800 764 766 and have label information ready.
If swallowed DO NOT induce vomiting. Give large quantities of water or milk. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and consult a doctor. Remove contact lenses if present and easy to do and continue rinsing. If skin contact causes irritation, remove contaminated clothing and wash skin thoroughly. If breathing difficulty arises remove to fresh air. Apply artificial respiration if not breathing.

SPECIAL Do not use below 10°C as drying will be inhibited and moisture entrapment will likely impair the finish.

INSTRUCTIONS: **NOTE:** Thorough stirring is essential before use due to the weight of the plastic granules (they tend to float) and have to be dispersed into the film before applying.